

# TEST REPORT MEASUREMENT OF ANTIBACTERIAL ACTIVITY OF TEXTURE PAINT

Request No: Q2-240328-03 Sample No: S2-240328-04 Report No: R2-240328-04

# Prepared for Vivant Space Trading LLC Dubai

**United Arab Emirates** 

Date of Request: Mar 28,2024 Sample Receiving Date: Mar 28,2024 Testing Initiated: April 06,2024 Testing Completed: April 18,2024 Report Issued: April 19,2024

Performed By: Pavithra CK

Title: Senior Microbiologist

Approved By: Manu P

Title: Laboratory Manager





Report No: R2-240328-04

# **OBJECTIVE**

According to the test request, the sample provided was to be tested for antibacterial activity against *Escherichia coli* ATCC 8739 and *Staphylococcus aureus* ATCC 6538 based on ISO 22196:2011 ("Measurement of antibacterial activity on plastics and other non-porous surfaces").

### SAMPLE DETAILS

Sample Description: Texture Paint

Brand: Silk plaster Origin: Lativia – Europe

Sole Dealer: Vivant Space Trading LLC.

### **EXPERIMENTAL CONDITIONS**

| Test Organism                        | Staphylococcus aureus ATCC # 6538                  |  |  |
|--------------------------------------|--|--|--|
|                                      | Escherichia coli ATCC # 8739                       |  |  |
| Sample Size                          | Plastic Flim (40 mm x 40 mm)- Coated with Texture  |  |  |
|                                      | Paint  |  |  |
| Method of Sterilization/Pre-Cleaning | None   |  |  |
| Laboratory Control Sample            | Untreated plastic control (40 mm x 40 mm x 0.05 mm |  |  |
|                                      | film)  |  |  |
| Dilution Medium Used                 | Sterile dilute nutrient broth as per standard      |  |  |
| Neutralizing Broth Used              | D/E Neutralizing Broth                             |  |  |
| Amount of Neutralizing Broth         | 10 mL  |  |  |
| Starting Inoculum Concentration      | Staphylococcus aureus (ATCC#6538):4.6 x 105CFU/ml  |  |  |
|                                      | Escherichia coli (ATCC # 8739): 5.5 x 105CFU/ml    |  |  |
| Amount of Inoculum                   | 0.4 mL   |  |  |
| Contact Time                         | 24 hours   |  |  |

## **TEST PROCEDURE SUMMARY**

The Test Sample provided by the sponsor Texture Paint was coated on a Plastic Flim and allow it to dry for 48 hrs. The specimen of 4 x 4 cm sample (Coated with Texture Paint) and laboratory control have been prepared for each strain. The control was tested in triplicate at Time = 0 and Time = 24 hours. The test samples were tested in triplicate at Time = 24 hours. Separately for each test strain, 0,4 ml of standardized culture at 2,5- $10 \times 10^5$  cells/ml has been added to the specimen then the inoculum has been covered and gently press down with a  $40 \times 40$  mm film so that the test inoculum spreads to, but does not leak beyond, the edges of the film. The specimens inoculated have been left for 24 h (contact time) in standard test condition. At t0 and after the specified contact time, each specimen has been recovered and neutralized with 10 ml of validated neutralizer; viable microorganisms have been enumerated by pour plate method on TSA at  $35\pm1^{\circ}$ C for 24 hours; then bacterial colonies from each dilution series have been counted and recorded and the Logarithmic reduction of bacteria from test sample versus laboratory control sample at specified contact time has been calculated.



Page 2 of 3



Report No: R2-240328-04

### CALCULATION OF THE ANTIBACTERIAL ACTIVITY

When the test is deemed valid, the antibacterial activity is calculated using following formula:

$$R = (U_t - U_0) - (A_t - U_0) = U_t - A_t$$

Where:

R is the antibacterial activity;

U<sub>0</sub>: average of the Log cells/cm<sup>2</sup>, recovered from laboratory control at t<sub>0</sub>;

Ut: average of the Log cells/cm², recovered from laboratory control after 24h;

At: average of the Log cells/cm<sup>2</sup>, recovered from test sample after 24 h.

### **TEST RESULTS**

Average number of viable bacteria recovered from each specimen expressed as CFU/cm $^2$  and value of  $U_0$ ,  $U_t$  and  $A_t$  calculated

| Strain                                  | Contact time     | Specimen                    | Geometric mean (CFU/cm²) | Log CFU/cm <sup>2</sup> |
|---|------------------|-----------------------------|--------------------------|-------------------------|
| S. aureus                               | $t_0$            | Untreated (U <sub>0</sub> ) | 1.1 x 10 <sup>4</sup>    | 4.0                     |
|   | $T_{24l1}$       | Untreated (Ut24h)           | 3.1 x 10 <sup>3</sup>    | 3.3                     |
|   |                  | Treated (At24h)             | <1                       | <0                      |
| E. coli t <sub>0</sub> T <sub>24h</sub> | $t_0$            | Untreated (U <sub>0</sub> ) | 1.6 x 10 <sup>4</sup>    | 3.2                     |
|   | T <sub>24h</sub> | Untreated (Ut24h)           | 4.3 x 10 <sup>3</sup>    | 3.6                     |
|   |                  | Treated (At24h)             | <1                       | <0                      |

Antibacterial activity calculated as Log Reduction and % Reduction

| Strain    | t (h) | Log Reduction | % Reduction |
|-----------|-------|---------------|-------------|
| S. aureus | 24h   | >3.3          | >99.96      |
| E. coli   |       | >3.6          | >99.97      |

### **CONCLUSIONS**

On the basis of the obtained results, in compliance with the validity criteria, can be stated that the test sample tested at 24 hours of contact time, has antimicrobial activity (Log reduction > 2 Log) against S. aureus and E. coli, respectively in adopted experimental conditions.

\*End of Report

This report shall not be reproduced, unless in its entirety, without written approval from Testhub Laboratories. The results relate only to the material or product analyzed

Page 3 of 3